

High Technology, The end of the evolution

THE BEGINNING OF REAL DIGITY

Experience the evolution of styling and performance with Clif Designs window tinting films.

CLIF DESIGNS WINDOW TINT FILM

PRODUCT PERFORMANCE

모델	가시광선투과율(VLT)	색상	반사형태	소재	두께/구조	품질보증
CERAMIC XT	70 / 80	Soft Blue	비반사	Premium Ceramic	2mil / 2ply	10year
CERAMIC SP	10 / 20 / 35 / 50	Medium Black	비반사	Premium Ceramic	2mil / 2ply	10year
CERAMIC ST	5 / 15 / 20 / 25 / 35 / 85	Dignified Black	비반사	Ceramic	1.5mil / 2ply	7year
METAL RN	5 / 10 / 30 / 50	Refined Natural	메탈/반사	Sputter Metal	2mil / 2ply	10year
PEARL SILVER	5 / 10 / 15	Fascinating Pearl	비반사	Pearl Ceramic	1.5mil / 2ply	7year

모델	차단율(%)					반사율(IN/OUT)
	자외선(UVR)	(적외선)IRR	차폐계수(SC)	열취득계수(SHGC)	총태양에너지(TSER)	
CERAMIC XT	99.9	89~76	0.42~0.56	0.37~0.49	63~51	8
CERAMIC SP	99.9	81~79	0.27~0.40	0.24~0.35	76~65	7~8
CERAMIC ST	99.9	66~49	0.34~0.76	0.30~0.67	70~33	6~9
METAL RN	99.9	96~92	0.16~0.33	0.14~0.29	86~71	10~14
PEARL SILVER	99.9	88~50	0.34~0.51	0.30~0.45	70~55	7

* 성능 수치는(측정 기준 : 3.2mm Clear glass / 장비 : EDTM) 소비자의 이해와 선택을 돕기 위한 것으로, 측정 조건에 따라 오차율 (3 ~5%)을 가질 수 있습니다.